



Product Information Sheet

- Product:** PRO – FUSION H834 – 30 Resin
- Product Code:** 351 – 55288 - PL
- Sizes:** 20kg & 200kg
- Uses:** Pro-Fusion H834-30 is a low shrink, DCPD modified, promoted unsaturated polyester resin, which is ideally suited to the production of high-quality laminates. It has excellent wet out qualities and is designed for infusion moulding applications, it can also be used in RTM Lite. Pro-Fusion H834-30 has low exotherm and low shrinkage in thick sections making this resin ideal for large structures.
- Application:** Resin infusion and RTM Lite
- Features:** Low viscosity
 Low profile curing properties
 Low exotherm in thick infused laminate sections
 Excellent flow and glass wet out properties
 Reduced fibre print-through
 Improved gelcoat surface cosmetics

Typical Properties:

Appearance	Yellow-Green Liquid
Viscosity at 25°C	150 - 200cP
Gel time 1.5% @ 23°C	25 – 30 mins
Density	1.10 g/m ³
Flash Point	31°C
Barcol hardness	40

- Storage:** Store in a locked secure dangerous goods area in a tightly closed container away from any heat source, ignition source and out of direct sunlight, store below 25°C.
- Stability:** When stored correctly, a storage life of 6 months is expected.

Hazards:



Flammable



Health Hazard



Irritant

Personal Protection:



Enquires:

HS Composites Ltd
63 Hunua Road, Papakura, Auckland 2110
+64 (09) 295 2200
sales@hscomposites.co.nz
www.hscomposites.co.nz

For further information check the full SDS for this product.

10/21

Disclaimer: The information given in this data sheet is given in good faith and is believed to be valid and accurate at the time of publication. However, no responsibility is accepted for accident or injury which may occur from omissions or from information contained in the data sheet.