

Product Information Sheet Marine Putty LV

Product:	Synthepol Marine Putty LV P926MF
Uses:	Bonding stringers, coving corners, filling & bonding sanded GRP parts.
Application:	Trowel, putty knife or icing (cake) bag.
Features:	Extremely flexible and tough when cured, excellent adhesion to sanded GRP, lighter weight than most putties, MEKP cured, non-slumping.
Typical	Appearance in can of-white to light blue.
Properties:	Viscosity at 25°C is between 4 – 5 ps. Specific Gravity is 0.8 Flammability is High. Flash Point is 31°C. Shelf stability 6 months
Gel Time:	at 25°C with 2% MEKP – 18 – 24 mins
Storage:	Store in a secure area in closed container away from any heat source, ignition source and out of direct sunlight, store below 25°C.
Directions for Use:	Synthepol Marine Putty LV should be catalysed between 1.5% and 2% MEKP and mixed thoroughly before application. When used to bond components together we recommend that tests are carried out to ensure this product is suitable for the intended purpose.



Hazards:



Personal Protection:

For further information check the full SDS for this product.

Disclaimer: The information given in this data sheet is given in good faith and is believed to be valid and accurate at the time of publication. However, no responsibility is accepted for accident or injury which may occur from omissions or from information contained in the data sheet. 06/20