

Product Information Sheet

Product:	Synthepol P812 – Iso/NPG Gelcoat
Uses:	General mouldings, building, transport
Application:	Normally by spraying (pressure-pump systems or pressure pot)
Features:	Available in a wide range of colours
Typical	Viscous liquid (colour varies)
Properties:	Viscosity at 25°C is between 10,000 – 20,000cps Specific Gravity is 1.2 – 1.3 Flammability is High. Flash Point is 32°C. Storage stability – 6 months
Gel Time:	at 25°C with 1% MEKP – 8 – 16 minutes
Storage:	Store in a secure area in closed container away from any heat source, ignition source and out of direct sunlight, store below 25°C.
Directions for Use:	Synthepol P812 range of Iso/NPG gelcoats are formulated for use with 1 – 2% medium reactivity MEKP, workshop temperatures should be maintained above 15°C to ensure a satisfactory cure is achieved. The gelcoat should be applied in 3 even coats to achieve a recommended wet-film thickness of 0.6 – 0.65mm (23 – 25 thou).



Hazards:



Personal Protection:

For further information check the full SDS for this product.

Disclaimer: The information given in this data sheet is given in good faith and is believed to be valid and accurate at the time of publication. However, no responsibility is accepted for accident or injury which may occur from omissions or from information contained in the data sheet. 06/20