

Product Information Sheet

- Product:** Synthepol P816 Range Gelcoats
- Uses:** Architectural panels/marine/pontoons & buoys/recreational vehicles and general moulding.
- Application:** Normally sprayed with pressure-pump system or pressure pot is best.
- Features:** Available in a wide range of colours.
- Properties:** Viscosity at 25°C is between 10,000 – 20,000 cps
Specific Gravity is 1.2 – 1.3
Flammability is High. Flash Point is 28°C.
- Gel Time:** at 25°C with 1% MEKP – 8 – 16 mins
- Storage:** Store in a secure area in closed container away from any heat source, ignition source and out of direct sunlight, store below 25°C.
- Directions for Use:** Synthepol P816 Range of Iso/NPG gelcoats are formulated for use with 1 – 2% medium reactivity MEKP. Workshop temperature should be maintained above 15°C to ensure a satisfactory cure is achieved. The correct thickness is important to obtain a satisfactory cure, the gelcoat should be applied in 3 even passes obtaining a wet-film thickness of 0.6 – 0.65mm (23 – 25 thou).



Hazards:



Personal Protection:

For further information check the full SDS for this product.

Disclaimer: The information given in this data sheet is given in good faith and is believed to be valid and accurate at the time of publication. However, no responsibility is accepted for accident or injury which may occur from omissions or from information contained in the data sheet. 06/20